



PRODUCT DATA SHEET

CERAL MASTIC-2004

(Ceramic Insulating Mastic)

CERAL MASTIC 2004 is of highly insulating property so reduces temperature drop to a considerable extent.

CERAL MASTIC 2004 is non wettable to Molten Aluminium and of "IN SITU" hardening property.

CERAL MASTIC 2004 is very much helpful in implementing 'CLEAN METAL PRACTICE'

APPLICATION :-

Make studs of 2 to 3 mm dia. and length 6 to 8 m.m on vertical walls of M.S.Shell providing 2 to 3 inch distance between each stud.

Apply the CERAL MASTIC 2004 in moist condition on M.S. Shell to a 15 to 20mm thickness.

Air dry for 48 hours.

Apply/fill the CERAL MASTIC 2004 wherever the minute cracks found.

Air dry for 24 hours

Shape to be torched/pre-heated with hot dross.

Smaller shapes can be Oven Dried.

Preheat the shape, ready for use.

SHELF LIFE - Three Months From The Date Of Manufacturing

SAFETY PRECAUTION -Store The Container In Cool & Dry Place.

STANDARD PACKING : 6Kg. PC.